

SPECIFICATION FOR APPROVAL

1. Material

Production:	High Flux Cores
KDM.P/N:	KH301-026A
AL:	37(nH/N ²) ± 8%
Material:	26 μ
Coating Color:	Khaki
Coating material:	epoxy
Coating Breakdown Voltage:	1500V, 0.5mA, 2Sec




2. Physical Characteristics

Before Coating			After Coating			Le(cm)	Ae(cm ²)	V(cm ³)	W(cm ²)	Weight (g) (ref.)	Box Quantity (Pieces)
OD(Max.) in/mm	ID(Min.) in/mm	Ht(Max.) in/mm	OD(Max.) mm	ID(Min.) mm	Ht(Max.) mm						
3.063 77.80	1.937 49.20	0.626 15.90	78.90	48.20	17.02	19.950	2.270	45.300	18.237	340.4	54


3. Electrical Parameters(Typical) Temperature(25°C ± 2°C)

Test Item	Test Condition	Value(Typical)	Test Instrument
Inductance	φ 1.2mm/106Ts, 20kHz/1V, I=0A (Evenly full windings)(均匀绕满)	415.7 μ H ± 8%	CH3302
DC-Bias	φ 1.2mm/106Ts, 20kHz/1V, I=45A(H=300Oe) (Evenly full windings)(均匀绕满)	256.2 μ H (Min.)	WK3255B+WK3265B
	φ 1.2mm/106Ts, 20kHz/1V, I=60A(H=400Oe) (Evenly full windings)(均匀绕满)	195.0 μ H (Min.)	
Core Loss	50kHz/1000Gs	550mW/cm ³ (Max.)	SY-8219
Remarks	Set the internal resistance of LCR meter to 100 Ω .(电感测试仪内阻设置100 Ω)		

Core Loss Curves(Typical)



DC-Bias Curves(Typical)



KDM确认栏
KDM
Signature

科达磁电
技术部

客户确认栏
Customer
Signature

请在5个工作日内回签承认书，否则此承认书将作为后续订单的OQC标准。若有疑问，请及时联系我司RD部门。
Please sign back after approval within 5 working days, otherwise this approval sheet would be taken as OQC standard for subsequent orders. If you have any questions, please contact RD department in time.